

**Transparent and water clear curing compound for industrial flooring and colored concrete**

**Application**

- Curing compound for aesthetic concrete surfaces that in there “plastic” phase are submitted to atmospheric conditions

**Properties**

- Based on a selection of resin.
- Forms a thin water damp barrier 20 minutes after application.
- Protects against a premature drying out of the concrete due to a serious diminution of waterloose, caused by a combination of sunrays, low relative humidity and wind.
- The risk of plastic shrinking cracks is reduced impressionable and the properties of the concrete are optimized.
- Does not affect the aesthetic aspect of the concrete.

**Directions**

**Work method**

- Apply homogeneous, just after evaporation of the “bleeding” water.
- **Curing TR** is easy to spray on.

**Technical characteristics**

Form	liquid
Color	transparent
Density	+/- 0,82 kg/ltr

**Quantity to use**

0,100 – 0,120 ltr/m<sup>2</sup>

**Packaging**

25 ltr, 200 ltr and 1000 ltr

**Safety information – Transport – Handling and storage - Waste**

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

**Transport and storage**

Transport and store away from frost. Protect the product and its packaging against direct sunlight. Avoid storage at temperatures >30°C.

**Storage life**

1 year after manufacturing in the original closed packaging.

**Considerations**

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.