

Mineral pigments for colouring the Monulime lime based repair mortar for natural stone and bricks

Application

- For colouring the Monulime repair mortar

Properties

- Perfectly compatible with Monulime.
- Mixes well in the mortar.
- Colourfast.
- Mineral based.

Directions

Preparation

- Some pigments tend to clump together. Make sure to finely grind them or sieve them out.
- Test in advance how much pigment is needed to achieve the desired colour. Bear in mind that the final colour will only appear after the mortar has completely dried out.

Work method

- Add the pigments (possibly ground or sieved in advance) to the Monulime powder.
- Then mix the mortar as described in the Monulime technical data sheet.

Important remarks

- The amount of pigment added depends on the desired colour. All pigments can be combined with one another. Exact amounts are determined by you on site, but we can give you some guideline values:
 - Orange: between 2,00 and 5,00 m%
 - Blood red: between 0,50 and 2,50 m%
 - Ochre: between 0,25 and 3,00 m%
 - Black: between 0,01 and 0,50 m%
 - Carbon black: between 0,50 and 3,00 m%
 - Light brown: between 0,30 and 1,00 m%
 - Sienna: between 0,20 and 6,00 m%
 - Light blue: between 0,20 and 1,00 m%
- The final colour will not appear until after the mortar has completely dried.

Colors

Type O: Orange, Blood Red, Ochre, Black, Brown Wash, Brown, Light Brown

Type A: Sienna, Light Blue

Quantity to use

- Type O: max 5 m%
- Type A: max 15 m%

Packaging

Pot of 400 gram

Safety information – Transport – Handling and storage - Waste

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

Transport and storage

Store the product and its packaging dry and protect against moisture.

Storage life

1 year after manufacturing in the original closed packaging.

Considerations

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.