

Universal release agent for all common formwork materials**Application**

- Chemical release agent for concrete
- For wooden, metal or synthetic formworks

Properties

- Protects the formwork through a chemical reaction with the alkaline components in the cement.
- Little odour (low emission).
- Allows for an easy release between the cast concrete and formwork.
- No caking of the concrete on the formwork.
- Does not adversely affect the concrete in terms of adhesion of any finishing layers such as paint, plaster, etc.
- Gives the concrete an even and uniform surface without air bubbles and cavities.
- No waiting times; concrete can be poured immediately after application.
- A rust inhibitor prevents steel formwork from rusting.

Directions**Work method**

- Spray evenly **Formoil VX/LE** on the formwork just before pouring the concrete.
- **Formoil VX/LE** is preferably applied by spray method.
- **Formoil VX/LE** can also be applied with a brush or a cloth.

Technical characteristics

Aspect	liquid
Colour	yellow-brown
Density	0,81 – 0,90 kg/ltr
Flash point	>60°C

Quantity to use

Formwork with high porosity	25 up to 30 g/m ²
Formwork with mid porosity	15 up to 20 g/m ²
Formwork with low/no porosity	8 up to 15 g/m ²

Packaging

25 ltr, 210 ltr, 1000 ltr

Safety information – Transport – Handling and storage - Waste

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

Transport and storage

Transport and store away from frost. Protect the product and its packaging against direct sunlight. Avoid storage at temperatures >30°C.

Storage life

1 year after manufacturing in the original closed packaging.

Considerations

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.