

### Bond retarder-stabilizer for ready-to-use mortars

#### Application

- Product to be added to all mortars where a longer processing time is needed: pointing mortar, masonry mortar

#### Properties

- Liquid retarder-stabilizer with 3 qualities:
  - o Bond retarder.
  - o Plastifier.
  - o Air bubble former.
- Prevents time and material waste:
  - o When re-starting the work a fresh mortar is available.
  - o When interrupting the work the material is easy to clean.

#### Directions

##### Work method

- **Mortelretarder** is ready-to-use.
- Add **Mortelretarder** to the gauging water.
- Quantity to use: 0,6 up to 2,4% of the cement weight.
- Mixing time: mix the mortar for at least 3 minutes.
- To prepare mortar for brick laying, ordinary sand suffices (fineness up to 2,5). For brick jointing, finer sand is needed (1,5 to 2).
- To facilitate smoothing of the joints, it can be repointed by adding a filler.

##### Important remarks

- Any stabilized mortar may dry out. Carefully cover the mortar with foil during storage to avoid losing water through evaporation.
- Overdosing is possible. The correct dosage is determined through testing, as it depends on the nature of the components of the concrete, the desired quality and the weather conditions.

#### Technical characteristics

Color	brown
Aspect	liquid
Density	+/- 1,18 kg/ltr +/- 0,02
pH	8,0 +/- 1,0
Cl-ion content	less than 0,10%

#### Quantity to use

0,6 up to 2,4 % of the cement weight depending of the desired result

#### Packaging

20 kg, 1000 kg

**Safety information – Transport – Handling and storage - Waste**

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

**Transport and storage**

Transport and store away from frost. Protect the product and its packaging against direct sunlight. Avoid storage at temperatures >30°C.

**Storage life**

1 year after manufacturing in the original closed packaging.

**Considerations**

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.