

**Mortar oil, air entrainer for mortar and concrete****Application**

- Mortar oil, to be added to mortars to improve processing and frost resistance

**Properties**

- Ready-to-use, add to gauging water.
- Creates minuscule stable air bubbles in the mortar, making it easier to work.
- Significantly reduces segregation.
- Longer processing time.
- The adhesion of the mortar in the plastic phase is considerably increased without causing it to stick.

**Directions****Work method**

- Add **Remix** to the gauging water.
- Dosage: 0,2 up to 0,4% of the cement weight (= 100 up to 200 ml per 50 kg cement).
- The maximum dosage can no overrun of 0,4% of 200 ml per 50 kg cement.
- Prepare the mortar with this gauging water and apply.

**Technical characteristics**

Colour	colourless
Aspect	liquid
Solvent	water
pH	8
Density	+/- 1,0
Boiling point	100°C

**Quantity to use**

0,2 till max. 0,4% of the cement weight i.e. 100 à 200 ml per 50 kg cement

**Packaging**

10 ltr, 25 ltr, 200 ltr

**Safety information – Transport – Handling and storage - Waste**

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

**Transport and storage**

Transport and store away from frost. Protect the product and its packaging against direct sunlight. Avoid storage at temperatures >30°C.

**Storage life**

2 years after manufacturing in the original closed packaging.

**Considerations**

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.