

**Powder to stop leaks, even under water pressure (hardens in 1 minute)****Application**

- Stops leaks and fills up cracks in concrete or masonry
- Even under water pressure

**Properties**

- Rapidly binding.
- Mineral polymer modified.
- Hardens in 1 minute.
- Ready to use.

**Directions****Preparation**

- The surface must be firm, sound and clean. Make sure that the surface is dry enough and free of dubious and loose layers.
- If necessary, one has to hew the crack into a dovetail joint, until one reaches a solid base.

**Work method**

- Mix a little **Redivit** powder with a bit of water.
- Keep the mush pressed firmly into the crack and press until complete hardening.
- If necessary, repeat until the leak is completely closed.

**Important remarks**

- **Redivit** can not be used as end-layer or final sealing. **Redivit** must always be overlaid with waterproofing mortar or masonry for example Cemsec.
- Use gloves in order to protect the skin, avoid contact with the eyes.

**Technical characteristics**

Aspect	powder
Drying time	+/- 1 minute

**Quantity to use**

As needed

**Packaging**

5 kg, 10 kg and 25 kg

**Safety information – Transport – Handling and storage - Waste**

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

**Transport and storage**

Store the product and its packaging dry and protect against moisture.

**Storage life**

9 months after manufacturing in the original closed packaging.

**Considerations**

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.