

Solvent free curing compound based on wax for industrial flooring and colored concrete

Application

- Curing compound for aesthetic concrete species that in there “plastic” phase are submitted to atmospheric conditions

Properties

- Based on a selection of resin.
- Forms a thin water damp barrier after application.
- Protects against a premature drying out of the concrete due to a serious diminution of waterloose, caused by a combination of sunrays, low relative humidity and wind.
- The risk of plastic shrinking cracks is reduced impressionable and the properties of the concrete are optimized.

Directions**Work method**

- Apply homogeneous, just after evaporation of the “bleeding” water.
- **Aquacure PB** is easy to spray on.

Technical characteristics

| | |
|---------|-----------------|
| Form | liquid |
| Color | milky white |
| Density | +/- 0,99 kg/ltr |

Quantity to use

0,100 – 0,150 ltr/m²

Packaging

20 ltr, 190 ltr, 900 ltr

Safety information – Transport – Handling and storage - Waste

Consult the most recent and product-related safety information sheet from Rewah in compliance with the (EU) 453/2010 annex II/A guidelines. The information on the abovementioned safety information sheet has been drawn up with the greatest care and is based on the knowledge available at the date of issue. We accept no liability for damage or hindrance of any kind which could be caused by the use of the product concerned.

Transport and storage

Transport and store away from frost. Protect the product and its packaging against direct sunlight. Avoid storage at temperatures >30°C.

Storage life

6 mois after manufacturing in the original closed packaging.

Considerations

The data included in this sheet, the application advices and other recommendations are based on extensive research and experience. They are however not binding also in relation to third party liability. They do not protect the customer against checking the products and directions for their suitability for the purpose. The characteristics and properties described are average values and analyses registered at 20°C, variances are tolerated. Our customer service will gladly answer your questions. The rewrite of this sheet replaces all previous sheets.